


AFD: 23.0 μ
SD: 5.0 μ
CV: 21.5 %
CF: 91.7 %
Curve: 40.3 Dg/mm
Min: 22.2 μ
Max: 25.7 μ
Staple: 85.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

AFD: 23.0 μ
SD: 5.0 μ
CV: 21.5 %
CF: 91.7 %
Curve: 40.3 Dg/mm
Min: 22.2 μ
Max: 25.7 μ
Staple: 85.0 mm

